



Creating Performance Solutions

13929 East 166th Street • Cerritos, California, USA 90702-7666 • Tel (562) 926-1010 • Fax (562) 926-9486 • www.iccink.com

PRODUCT NUMBER	RECOMMENDED FABRICS	BLEED RESISTANCE	DRYER TEMPERATURES	OPACITY	FLASH	MESH
----------------	---------------------	------------------	--------------------	---------	-------	------

For Cotton

7005 Knock Out Cotton White™	100% Cotton	100% Cotton Only	325°F (163°C)	Very Good	Very Good	60-230 Monofilament
-------------------------------------	-------------	------------------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, high pigment, fast flashing, low tack, high performance plastisol screen printing ink. Suitable for both auto and manual presses for use on 100% Cotton Fabrics.

7038 Blaze Cotton White™	100% Cotton	100% Cotton Only	325°F (163°C)	Excellent	Very Good	86-230 Monofilament
---------------------------------	-------------	------------------	---------------	-----------	-----------	---------------------

Comments: Newly reformulated Non-Phthalate, high pigment white with a very creamy, short body that is easy to print. Economically priced white plastisol for use on 100% Cotton fabrics.

For Cotton and 50/50 Cotton/Polyester Blend

711 Classic White™	100% Cotton Cotton/Polyester Blends	Very Good	325°F (163°C)	Excellent	Excellent	86-230 Monofilament
---------------------------	-------------------------------------	-----------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, optically brightened, high pigment white that is low fusing and fast flashing. Product contains no bleaching agents. When fusing at low temperatures (300°F or less), allow for longer time in dryer in order for entire ink film to reach temperature.

7007 Knock Out Low Bleed White	100% Cotton Cotton/Polyester Blends	Average	325°F (163°C)	Very Good	Very Good	60-230 Monofilament
---------------------------------------	-------------------------------------	---------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, Low Bleed, high pigment, fast flashing, low tack ink with a creamy viscosity and medium body. Suitable for both auto and manual presses. Offers superior performance through fast production speeds and its brightness and opacity.

7014 Legacy White™	100% Cotton Cotton/Polyester Blends	Very Good	325°F (163°C)	Excellent	Excellent	86-230 Monofilament
---------------------------	-------------------------------------	-----------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, high pigment low bleed white that is low fusing and fast flashing. Product contains no bleaching agents. When fusing at low temperatures (300°F or less), allow for longer time in dryer in order for entire ink film to reach temperature.

7031 Ultra White™	100% Cotton	Average	325°F (163°C)	Excellent	Very Good	86-305 Monofilament
--------------------------	-------------	---------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, very optically bright white with a very creamy, short body. Low tack product that is suited for high definition print on automatic printing equipment. Not recommended for use in marginal drying conditions.

7041 Paramount White™	Cotton/Polyester Blends 100% Polyester	Excellent	325°F (163°C)	Excellent	Very Good	86-230 Monofilament
------------------------------	--	-----------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, ultra low bleed white formulated to help block dye migration problems on various problem polyester content fabrics.

7042 Blaze Low Bleed White™	100% Cotton Cotton/Polyester Blends	Very Good	325°F (163°C)	Very Good	Very Good	60-230 Monofilament
------------------------------------	-------------------------------------	-----------	---------------	-----------	-----------	---------------------

Comments: Non-Phthalate, low bleed, high pigment, fast flashing, low tack, plastisol screen printing ink. Economically priced white plastisol for use on Cotton/Polyester fabrics.



Creating Performance Solutions

13929 East 166th Street • Cerritos, California, USA 90702-7666 • Tel (562) 926-1010 • Fax (562) 926-9486 • www.iccink.com

PRODUCT NUMBER	RECOMMENDED FABRICS	BLEED RESISTANCE	DRYER TEMPERATURES	OPACITY	FLASH	MESH
----------------	---------------------	------------------	--------------------	---------	-------	------

For Polyester

741 Poly White	Cotton/Polyester Blends 100% Polyester	Excellent	325°F (163°C)	Good	Very Good	86-160 Monofilament
-----------------------	---	-----------	---------------	------	-----------	------------------------

Comments: Non-Phthalate, ultra low bleed white formulated to help block dye migration problems on various problem polyester content fabrics.

For Mixing

7538 Ultramix® Mixing White	100% Cotton Cotton/Polyester Blends	Average	325°F (163°C)	Very Good	Very Good	110-305 Monofilament
------------------------------------	--	---------	---------------	-----------	-----------	-------------------------

Comments: Non-Phthalate, mixing white with a very creamy, short body. Low tack product that is well suited for high definition and halftone prints on automatic printing equipment. Part of the UltraMix® 7500 Series Pantone® Color System.

9201 Ultramix® Nylon Mixing White	Nylon	Average	325°F (163°C)	Very Good	Very Good	110-305 Monofilament
--	-------	---------	---------------	-----------	-----------	-------------------------

Comments: Non-Phthalate, quick flashing, 2-part mixing white for printing onto normally hard to print nylon fabrics. Well suited for fine detail and halftone printing using finer mesh screens.. Part of the UltraMix® 9000 Series Pantone® Color System.

For Specific Printing Purpose

12 High Pigment White	100% Cotton	100% Cotton Only	325°F (163°C)	Very Good	Good	60-230 Monofilament
------------------------------	-------------	------------------	---------------	-----------	------	------------------------

Comments: Non-Phthalate, high pigment white for use on 100% Cotton as a direct print or cold peel transfer ink.

901 Nylon White	Nylon	Average	325°F (163°C)	Very Good	Very Good	86-305 Monofilament
------------------------	-------	---------	---------------	-----------	-----------	------------------------

Comments: Non-Phthalate, high pigment white formulated for use with 900 Catalyst to print on nylon fabrics. Can also be used with powder adhesive, to make cold peel transfers for use on open mesh nylon fabrics. Transfer application: 305°F to 375°F (180°C to 190°C), 10 to 12 seconds, cool or cold peel.

7043 Guardian Gray™	Cotton/Polyester Blends 100% Polyester Performance Fabrics	Excellent	285°F to 325°F (140°C to 163°C)	Excellent	Very Good	60-230 Monofilament
----------------------------	--	-----------	------------------------------------	-----------	-----------	------------------------

Comments: Non-Phthalate, excellent bleed resistant under base ink. Use to help block dye migration on problem fabrics that contain polyester, including sublimated dyed fabrics.

7113 Performance Pro™ White	Cotton/Polyester Blends 100% Polyester Performance Fabrics	Excellent	285°F to 300°F (140°C to 149°C)	Very Good	Very Good	60-230 Monofilament
------------------------------------	--	-----------	------------------------------------	-----------	-----------	------------------------

Comments: Non-Phthalate, high pigment white formulated for use on performance fabric.